



TECHNICAL DATA

TD-1353

PRODUCT NAME

PRODUCT NO.

INTERIOR ACRYLIC LATEX PAINT FOR CEILINGS – TITANIUM WHITE

171-112

DESCRIPTION

Latex flat finish specially formulated for use on ceilings.

INTENDED USES

Interior.
New or maintenance work.
Primed materials: gypsum or fibre wallboards, wood, plaster, metal, concrete, concrete blocks, acoustical tiles.
Ceilings.
Homes, institutions, schools, hospitals, commercial or public buildings.

REMARK: For kitchens and bathrooms, a platinum, melamine, pearl or semi-gloss finish is preferable.

ADVANTAGES

High viscosity and ultra hiding.
Ready for use and easy to apply.
Dries rapidly with a minimum of odour.
Ultra flat finish without any reflection.
Non-splattering.
Ecological product containing neither lead nor mercury and featuring the Canadian Environmental ECOLOGO as approved by the Canadian Standard Association (CSA).

SURFACE PREPARATION

PROPER SURFACE PREPARATION IS IMPORTANT.

The surface must be dry, clean, free from dust, oil, grease, soap, wax, mildew, rust, loose paint, etc. Wash well with a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137. Rinse well with clear water.

Mildew: Wash with bleach water. (1:3 bleach water: water)

Glossy surfaces: Sand lightly.

Bare wood: Seal knots and sap streaks with transparent shellac POLYPREP 205-112 or white-pigmented POLYPREP 2 (145-022).

Loose paint: Scrape, then sand. Prime bare spots with recommended primer.

Repair cracks and loose joints.

Rust: Remove with CORROSTOP ULTRA 635-104 metal conditioner and rust remover.

TD-1353

TECHNICAL GUIDE

VISCOSITY:	Ready for use.	COLOUR:	Titanium white	171-112
FLASH POINT:	Non-flammable.	TINTING:	Can be tinted, maximum 3 ounces of colorant per 3.78 litres.	
GLOSS (60°):	0 to 5 %	COMPOSITION:	Vinyl-acrylic latex (binder), titanium dioxide and inert extenders (pigments), water (volatile matter), surfactants (agents) and others.	
DRYING TIME:	1 to 2 hours.	STORAGE:	Keep between 4°C (40°F) and 26°C (80°F) in a safe and well-ventilated place. Avoid freezing.	
RECOATING:	4 hours. Vary according to temperature and relative humidity.	THINNER/ CLEANER:	Water	
SPREADING RATE:	10 to 12 square metres (110 to 130 sq. ft.) per litre depending on porosity and texture of the surface.	APPLICATION TOOLS:	Preferably a roller or a spray gun. Use a brush (nylon/polyester) for cutting in.	
SIZES:	3.78 litres and 946 ml.		Wash tools in warm soapy water immediately after use.	
SPECIFICATIONS:	None.			

RECOMMENDED PRIMER

Bare wood: Apply one coat of alkyd primer SICO CLASSIC 180-110 or latex 170-125.

Gypsum board, thoroughly dry new plaster, concrete and concrete blocks: Apply one coat of latex primer SICO CLASSIC 170-125.

Previously painted surfaces in good condition and plaster repairs: Apply one coat of alkyd primer SICO CLASSIC 180-110 or latex 170-125.

Old plaster: Apply one coat of alkyd primer SICO CLASSIC 180-110.

Ferrous metal: Apply one coat of anti-corrosion primer CORROSTOP ULTRA 635-260 or 635-785.

APPLICATION

Product ready for use. No thinning required.

Stir thoroughly before using. Provide adequate ventilation during application and drying.

Apply generously one coat and a second one the next day if necessary.

Apply generously and evenly.

Application temperature: Minimum 10°C (50°F), maximum 32°C (90°F).

Let dry thoroughly before recoating.

Washing instructions: Allow to dry fourteen (14) days before washing. Soil and most household stains can be removed using a soft cloth or sponge and a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137.

RESTRICTIONS

Do not use on surfaces subjected to frequent cleaning and scrubbing.

Do not use for exterior work.

Do not use on floors.

Do not use as an undercoater or primer-sealer.

SAFETY PRECAUTIONS

Do not swallow. Do not get in eyes or on skin. Wear safety glasses.

FIRST AID TREATMENT: If swallowed, call a Poison Control Centre or doctor immediately. If in eyes or on skin, rinse well with water.

Keep out of reach of children.

Paint disposal: Contact your municipality about proper paint disposal procedure.