



TECHNICAL DATA

TD-1365

PRODUCT NAME

PRODUCT NO.

INTERIOR ALKYD PAINT – PEARL FINISH – SUPER ALKYD.

186-XXX

DESCRIPTION

Subdued gloss paint for walls, ceilings, woodwork, doors of any room.
Subdued reflection when viewed straight on and semi-gloss when viewed at a grazing angle.

INTENDED USES

Interior.
New work or maintenance.
Primed materials: gypsum or fibre wallboards, wood, plaster, metal, concrete, concrete blocks.
On walls, ceilings, woodworks, doors, cabinets, kitchen furnitures.
Bathrooms, kitchens, laundry and any other room.
Homes, apartments, schools, offices, stores, hotels, hospitals.

ADVANTAGES

Complete range of colors.
Very good coverage, high hiding.
Smooth, uniform finish.
Soft surface that does not retain dirt.
Super adherent and resistant.
Ultra washable and scrubbable.
Ready for use, easy to apply and dries without unpleasant odor.
Contains no lead no mercury.

SURFACE PREPARATION

PROPER SURFACE PREPARATION IS IMPORTANT PARTICULARLY IN THE KITCHENS AND THE BATHROOMS.
The surface must be dry, clean and free from dust, oil, grease, soap, wax, mildew, rust, loose paint, etc.
Wash the surface well before painting with a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137.
Rinse well with clear water.
Mildew: wash with a household bleach solution. (1:3 household bleach: water)
Glossy surfaces: sand lightly.
Bare wood: seal knots and sap streaks with transparent shellac POLYPREP 205-112 or white pigmented POLYPREP 2 (145-022).
Loose paint: scrape, then sand. Prime bare spots with recommended primer.
Repair cracks and loose joints.
Rust: remove with CORROSTOP ULTRA 635-104 metal conditioner and rust remover.

TD-1365

TECHNICAL GUIDE

VISCOSITY:	Ready for use.	COLORS:	Titanium white 186-110, natural white 186-501 and intermediate base 186-502, neutral 186-503, yellow 186-504 and red 186-505.
FLASH POINT:	Min. 51°C (124°F).	TINTING:	Can be tinted to Sico 4000 colors system.
GLOSS (60°):	22 to 30%	COMPOSITION:	Alkyd resin (binder), titanium dioxide and inert extenders (pigments), driers (agents), deodorized mineral spirits (volatile matter).
REFLECTS (85°):	60 to 70%	STORAGE:	Keep between 4°C (40°F) and 26°C (80°F) in a safe and well ventilated place.
DRYING TIME:	30 to 60 minutes (to touch) 4 to 5 hours (tack free) 12 to 16 hours (recoat) Varies according to temperature and relative humidity.	THINNER	Mineral spirits POLYPREP 875-104.
SPREADING RATE:	Approx. 12m ² (130 sq. ft.) per litre depending on porosity and texture of the surface.	APPLICATION TOOLS:	Brush, roller or spray gun.
SIZES:	3.78 litres and 946 ml		
SPECIFICATIONS:	Type CAN/CGSB – 1.202-M92 Type 2.		Wash tools in thinner immediately after use.

RECOMMENDED PRIMER

Bare wood: Apply one coat of alkyd primer SICO CLASSIC 180-110 or latex 170-125.

Gypsum boards, dry new plaster, concrete and concrete blocks: Apply one coat of latex primer SICO CLASSIC 170-125.

Previously painted surfaces and plaster repairs: Apply one coat of alkyd primer SICO CLASSIC 180-110 or latex 170-125.

Previously painted surfaces, clean and in good condition: no primer required unless the surface is absorbent.

Old plaster: Apply one coat of alkyd primer SICO CLASSIC 180-110.

Ferrous metal: Apply one coat of CORROSTOP ULTRA anti-corrosion primer 635-260 or 635-785.

APPLICATION

Ready for use. No thinning required.

Stir thoroughly before using. Apply generously and evenly.

Application temperature: minimum 10°C (50°F), maximum 32°C (90°F).

Number of coats: two (2). LET DRY THOROUGHLY BETWEEN COATS.

Washing instructions: allow to dry for seven (7) days before washing. Soil and most household stains can be removed using a soft cloth or sponge and a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137.

RESTRICTIONS

Do not use for exterior work.

Do not use on floors.

Do not mix with other paints or thinner.

SAFETY PRECAUTIONS

Keep out of reach of children.

Keep away from open flame or spark.

Provide adequate ventilation during application and drying. Do not breathe vapors.

Keep containers closed when not in use.

FIRST AID TREATMENT: contains mineral spirits. If swallowed, do not induce vomiting.

Call a physician or poison control centre immediately.

Paint disposal: contact your municipality about proper paint disposal procedure.