



TECHNICAL DATA

TD-1850

PRODUCT NAME

PRODUCT NO.

INTERIOR ACRYLIC LATEX PAINT – PLATINUM FINISH – SUPER LATEX.

714-XXX

DESCRIPTION

A new finish reflecting the most recent decorating trends; suitable for any room of the house.
Soft, smooth, glare-free finish.

INTENDED USES

Interior.
New work or maintenance.
Primed materials: gypsum or fibre wallboards, wood, plaster, metal, concrete, concrete blocks, acoustical tiles, wallpaper.
Walls, ceilings, woodworks, doors, cabinets.
Any room in the house, schools, hospitals, commercial or public buildings.

ADVANTAGES

Ultra washable.
High viscosity and ultra hiding.
Ready for use and easy to apply.
Dries rapidly with a minimum of odor.
High resistance to washing, scrubbing and yellowing.
Complete range of colors.
Ecological product containing no lead no mercury and featuring the Canadian Environmental ECOLOGO as approved by the Canadian Standard Association (CSA).

SURFACE PREPARATION

PROPER SURFACE PREPARATION IS IMPORTANT PARTICULARLY IN THE KITCHENS AND THE BATHROOMS. The surface must be dry, clean and free from dust, oil, grease, soap, wax, mildew, rust, loose paint, etc. Wash the surface well before painting with a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137. Rinse well with clear water.
Mildew: wash with a household bleach solution. (1:3 household bleach: water)
Glossy surfaces: sand lightly.
Bare wood: seal knots and sap streaks with transparent shellac POLYPREP 205-112 or white pigmented POLYPREP 2 (145-022).
Loose paint: scrape, then sand. Prime bare spots with recommended primer. Repair cracks and loose joints.
Rust: remove with CORROSTOP ULTRA 635-104 metal conditioner and rust remover.

TD-1850

TECHNICAL GUIDE

VISCOSITY:	Ready for use.	COLORS:	Super white 714-110, natural white 714-501 and intermediate base 714-502, neutral 714-503, yellow 714-504 and red 714-505.
FLASH POINT:	Non-flammable.	TINTING:	Can be tinted to Sico 4000 colors system.
GLOSS (60°):	12 to 22%	COMPOSITION:	Modified acrylic latex (binder), titanium dioxide and inert extenders (pigments), water (volatile matter), surfactant (agents) and others.
REFLECTS (85°):		STORAGE:	Keep between 4°C (40°F) and 26°C (80°F) in a safe and well ventilated place.
DRYING TIME:	20 to 30 minutes (to touch) 2 to 4 hours (tack free) 4 to 6 hours (recoat) Varies according to temperature and relative humidity.		Avoid freezing.
SPREADING RATE:	11 to 13 m ² (120 to 140 sq. ft.) per litre depending on porosity and texture of the surface.	THINNER:	Water
SIZES:	3.78 litres and 946 ml	APPLICATION TOOLS:	Brush, roller or spray gun. Preferable a roller for large surfaces and a synthetic bristle (nylon/polyester) brush for trim.
SPECIFICATIONS:	None.		Wash tools in warm soapy water immediately after use.

RECOMMENDED PRIMER

Bare wood: Apply one coat of alkyd primer SICO SUPREME 720-110 or latex 710-120.

Gypsum boards, dry new plaster, concrete and concrete blocks: Apply one coat of latex primer SUPREME 710-120.

Previously painted surfaces and plaster repairs: Apply one coat of alkyd primer SUPREME 720-110 or latex 710-120.

Old plaster: Apply one coat of alkyd primer SICO SUPREME 720-110.

Ferrous metal: Apply one coat of CORROSTOP ULTRA anti-corrosion primer 635-260 or 635-785.

APPLICATION

Ready for use. No thinning required.

Stir thoroughly before using. Apply generously and evenly.

Allow to dry completely before recoating.

A second finishing coat application insures a better durability and appearance.

Application temperature: minimum 10°C (50°F), maximum 32°C (90°F).

Washing instructions: allow to dry for seven (7) days before washing. Soil and most household stains can be removed using a soft cloth or sponge and a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137.

RESTRICTIONS

Do not use for exterior work.

Do not use on floors.

SAFETY PRECAUTIONS

Keep out of reach of children.

Provide adequate ventilation during application and drying.

Keep containers closed when not in use.

Paint disposal: contact your municipality about proper paint disposal procedure.