



## TECHNICAL DATA

TD-1859

### PRODUCT NAME

### PRODUCT NO.

INTERIOR ALKYD PAINT FOR CEILINGS – FLAT FINISH.

721-112

### DESCRIPTION

Alkyd flat finish especially formulated for use on ceilings.

### INTENDED USES

Interior.  
New or maintenance work.  
Primed materials: gypsum or fibre wallboards, wood, plaster, metal, concrete, concrete blocks, acoustical tiles.  
Ceilings.  
Homes, institutions, schools, hospitals, commercial or public buildings.

REMARK: For kitchens and bathrooms, a platinum, melamine, pearl or semi-gloss finish is preferable.

### ADVANTAGES

High hiding.  
Ready for use and easy to apply.  
Dries rapidly with low odor.  
Ultra flat finish without any reflection.  
Non-spattering.  
Contains no lead nor mercury.

### SURFACE PREPARATION

PROPER SURFACE PREPARATION IS IMPORTANT.

The surface must be dry, clean, free from dust, oil, grease, soap, wax, mildew, rust, loose paint, etc. Wash well with a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137. Rinse well with clear water.

Mildew: wash with a household bleach solution. (1:3 household bleach: water)

Glossy surfaces: sand lightly.

Bare wood: seal knots and sap streaks with transparent shellac POLYPREP 205-112 or white-pigmented POLYPREP 2 (145-022).

Loose paint: scrape, then sand. Prime bare spots with recommended primer.

Repair cracks and loose joints.

Rust: remove with CORROSTOP ULTRA 635-104 metal conditioner and rust remover.

TD-1859

## TECHNICAL GUIDE

<b>VISCOSITY:</b>	Ready for use.	<b>COLORS:</b>	White	721-112
<b>FLASH POINT:</b>	48°C	<b>TINTING:</b>	Can be tinted, maximum 3 ounces of colorant COLORIZER per 3.78 litres.	
<b>GLOSS (60°):</b>	0 to 5%	<b>COMPOSITION:</b>	Alkyd resin (binder), titanium dioxide and inert extenders (pigments), driers (agents), deodorized aliphatic hydrocarbon.	
<b>DRYING TIME:</b>	1 to 2 hours (to touch) 6 to 8 hours (recoat) Varies according to temperature and relative humidity.	<b>STORAGE:</b>	Keep between 4°C (40°F) and 26°C (80°F) in a safe and well-ventilated place.	
<b>SPREADING RATE:</b>	11 to 13 m <sup>2</sup> (120 to 140 pi <sup>2</sup> ) per litre depending on porosity and texture of the surface.	<b>REDUCER:</b>	Mineral spirits POLYPREP 875-104.	
<b>SIZES:</b>	3.78 litres and 946 mL.	<b>APPLICATION TOOLS:</b>	Prefer roller or spray application. Also brush (nylon/polyester) for trim. Wash tools with thinner immediately after use.	
<b>SPECIFICATIONS:</b>	None.			

## RECOMMENDED PRIMER

Bare wood: Apply one coat of alkyd primer SICO SUPREME 720-110 or latex 710-120.

Gypsum boards, thoroughly dry new plaster, concrete and concrete blocks: Apply one coat of latex primer SICO SUPREME 710-120.

Previously painted surfaces in good condition and plaster repairs: Apply one coat of alkyd primer SICO SUPREME 720-110 or latex 710-120.

Old plaster: Apply one coat of alkyd primer SICO SUPREME 720-110.

Ferrous metal: Apply one coat of anti-corrosion primer CORROSTOP ULTRA 635-260 or 635-785.

## APPLICATION

Product ready for use. No thinning required.

Stir thoroughly before using.

Apply generously and evenly.

Application temperature: minimum 10°C (50°F), maximum 32°C (90°F).

Let dry thoroughly before recoating.

WASHING INSTRUCTIONS: allow to dry 7 days before washing.

## RESTRICTIONS

Do not use on surfaces subjected to frequent cleaning and scuffing.

Do not use for exterior work.

Do not use on floors.

Do not use as an undercoater or primer-sealer.

## SAFETY PRECAUTIONS

Keep out of reach of children.

Keep away from open flame or spark.

Provide adequate ventilation during application and drying. Do not breathe vapors.

Keep containers closed when not in use.

FIRST AID TREATMENT: contains mineral spirits. If swallowed, do not induce vomiting.

Call a physician or poison control centre immediately.

Paint disposal: contact your municipality about proper paint disposal procedure.