



TECHNICAL DATA

TD-1851

PRODUCT NAME

PRODUCT NO.

INTERIOR ALKYD PAINT – VELVET FINISH – SUPER ALKYD.

723-XXX

DESCRIPTION

Low gloss finish decorating walls and ceilings of bedroom, living room, dining room and boudoir.

REMARK: For kitchens and bathrooms, a pearl or semi-gloss finish is preferable.

INTENDED USES

Interior.
New work or maintenance.
Primed materials: gypsum or fibre wallboards, wood, plaster, metal, concrete, concrete blocks.
Walls and ceilings.
Homes, schools, churches, apartments, hospitals, offices, etc.

ADVANTAGES

Easy to apply.
Smooth, uniform finish.
High hiding.
Low odor.
Washable.
Complete range of colors.
Attractive look; reflection absence conceal surfaces imperfections.
Contains no lead, nor mercury.

SURFACE PREPARATION

PROPER SURFACE PREPARATION IS IMPORTANT PARTICULARLY IN THE KITCHENS AND THE BATHROOMS. The surface must be dry, clean and free from dust, oil, grease, soap, wax, mildew, rust, loose paint, etc. Wash the surface well before painting with a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137. Rinse well with clear water.
Mildew: wash with a household bleach solution. (1:3 household bleach: water)
Glossy surfaces: sand lightly.
Bare wood: seal knots and sap streaks with transparent shellac POLYPREP 205-112 or white pigmented POLYPREP 2 (145-022).
Loose paint: scrape, then sand Prime bare spots with recommended primer.
Repair cracks and loose joints.
Rust: remove with CORROSTOP ULTRA 635-104 metal conditioner and rust remover.

TD-1851

TECHNICAL GUIDE

VISCOSITY:	Ready for use.	COLORS:	Super white 723-110, natural white 723-501 and intermediate base 723-502, neutral 723-503, yellow 723-504 and red 723-505.
FLASH POINT:	Min. 51°C (124°F).	TINTING:	Can be tinted to Sico 4000 colors system.
GLOSS (60°):	5 to 12%	COMPOSITION:	Alkyd resin (binder), titanium dioxide and inert extenders (pigments), driers (agents), deodorized mineral spirits (volatile matter).
REFLECTS (85°):	20 to 30%	STORAGE:	Keep between 4°C (40°F) and 26°C (80°F) in a safe and well ventilated place.
DRYING TIME:	30 to 60 minutes (to touch) 2 hours (tack free) 6 to 8 hours (recoat) Varies according to temperature and relative humidity.	THINNER:	Mineral spirits POLYPREP 875-104.
SPREADING RATE:	Approx. 12 m ² (130 sq. ft.) per litre depending on porosity and texture of the surface.	APPLICATION TOOLS:	Brush, roller or spray gun.
SIZES:	3.78 litres and 946 mL		
SPECIFICATIONS:	Type CAN/CGSB – 1.202-M92 Type 1.		Wash tools with thinner immediately after use.

RECOMMENDED PRIMER

Bare wood: Apply one coat of alkyd primer SICO SUPREME 720-110 or latex 710-120.

Gypsum boards, dry new plaster, concrete and concrete blocks: Apply one coat of latex primer SICO SUPREME 710-120.

Previously painted surfaces and plaster repairs: Apply one coat of alkyd primer SICO SUPREME 720-110 or latex 710-120.

Previously painted surfaces, clean and in good condition: no primer required unless the surface is absorbent.

Old plaster: Apply one coat of alkyd primer SICO SUPREME 720-110.

Ferrous metal: Apply one coat of CORROSTOP ULTRA anti-corrosion primer 635-260 or 635-785.

APPLICATION

Ready for use. No thinning required.

Stir thoroughly before using. Apply generously and evenly.

Application temperature: minimum 10°C (50°F), maximum 32°C (90°F).

Number of coats: two (2). LET DRY THOROUGHLY BETWEEN COATS

Washing instructions: allow to dry for seven (7) days before washing. Soil and most household stains can be removed using a soft cloth or sponge and a concentrated solution of trisodium phosphate (T.S.P.) POLYPREP 771-137.

RESTRICTIONS

Do not use for exterior work.

Do not use on floors.

Do not mix with other paints or thinners.

SAFETY PRECAUTIONS

Keep out of reach of children.

Keep away from open flame or spark.

Provide adequate ventilation during application and drying. Do not breathe vapors.

Keep containers closed when not in use.

FIRST AID TREATMENT: contains mineral spirits. If swallowed, do not induce vomiting.

Call a physician or poison control centre immediately.

Paint disposal: contact your municipality about proper paint disposal procedure.